



ASM Aerospace Specification Metals Inc.



Contact Us

Aluminum 5052-O

Subcategory: 5000 Series Aluminum Alloy; Aluminum Alloy; Metal; Nonferrous Metal

Close Analogs:

Composition Notes:

Aluminum content reported is calculated as remainder.

Composition information provided by the Aluminum Association and is not for design.

Key Words: UNS A95052; ISO AlMg2.5; Aluminium 5052-O; AA5052-O

Component	Wt. %	Component	Wt. %	Component	Wt. %
Al	95.7 - 97.7	Mg	2.2 - 2.8	Other, total	Max 0.15
Cr	0.15 - 0.35	Mn	Max 0.1	Si	Max 0.25
Cu	Max 0.1	Other, each	Max 0.05	Zn	Max 0.1
Fe	Max 0.4				

Material Notes:

Data points with the AA note have been provided by the Aluminum Association, Inc. and are NOT FOR DESIGN.

Physical Properties	Metric	English	Comments
Density	<u>2.68 g/cc</u>	0.0968 lb/in ³	AA; Typical

Mechanical Properties

Hardness, Brinell	47	47	AA; Typical; 500 g load; 10 mm ball
Ultimate Tensile Strength	<u>193 MPa</u>	28000 psi	AA; Typical
Tensile Yield Strength	<u>89.6 MPa</u>	13000 psi	AA; Typical
Elongation at Break	<u>25 %</u>	25 %	AA; Typical; 1/16 in. (1.6 mm) Thickness
Elongation at Break	<u>30 %</u>	30 %	AA; Typical; 1/2 in. (12.7 mm) Diameter
Modulus of Elasticity	<u>70.3 GPa</u>	10200 ksi	AA; Typical; Average of tension and compression. Compression modulus is about 2% greater than tensile modulus.
Ultimate Bearing Strength	<u>345 MPa</u>	50000 psi	Edge distance/pin diameter = 2.0

Bearing Yield Strength	<u>131 MPa</u>	19000 psi	Edge distance/pin diameter = 2.0
Poisson's Ratio	0.33	0.33	
Fatigue Strength	<u>110 MPa</u>	16000 psi	AA; 500,000,000 cycles completely reversed stress; RR Moore machine/specimen
Machinability	<u>30 %</u>	30 %	0-100 Scale of Aluminum Alloys
Shear Modulus	<u>25.9 GPa</u>	3760 ksi	
Shear Strength	<u>124 MPa</u>	18000 psi	AA; Typical

Electrical Properties

Electrical Resistivity	<u>4.99e-006 ohm-cm</u>	4.99e-006 ohm-cm	AA; Typical at 68°F
------------------------	-------------------------	------------------	---------------------

Thermal Properties

CTE, linear 68°F	<u>23.8 μm/m-°C</u>	13.2 μin/in-°F	AA; Typical; Average over 68-212°F range.
CTE, linear 250°C	<u>25.7 μm/m-°C</u>	14.3 μin/in-°F	Average over the range 20-300°C
Specific Heat Capacity	<u>0.88 J/g-°C</u>	0.21 BTU/lb-°F	Estimated from trends in similar Al alloys.
Thermal Conductivity	<u>138 W/m-K</u>	960 BTU-in/hr-ft ² -°F	AA; Typical at 77°F
Melting Point	607 - 649 °C	1125 - 1200 °F	AA; Typical range based on typical composition for wrought products 1/4 inch thickness or greater
Solidus	<u>607 °C</u>	1125 °F	AA; Typical
Liquidus	<u>649 °C</u>	1200 °F	AA; Typical

Processing Properties

Annealing Temperature	<u>343 °C</u>	650 °F	holding at temperature not required
Hot-Working Temperature	260 - 510 °C	500 - 950 °F	

References for this datasheet.

Some of the values displayed above may have been converted from their original units and/or rounded in order to display the information in a consistent format. Users requiring more precise data for scientific or engineering calculations can click on the property value to see the original value as well as raw conversions to equivalent units. We advise that you only use the original value or one of its raw conversions in your calculations to minimize rounding error.