



ASM Aerospace Specification Metals Inc.



Contact Us

## Aluminum 5083-H112

**Subcategory:** 5000 Series Aluminum Alloy; Aluminum Alloy; Metal; Nonferrous Metal

### Close Analogs:

### Composition Notes:

Aluminum content reported is calculated as remainder.

Composition information provided by the Aluminum Association and is not for design.

**Key Words:** UNS A95083; ISO AlMg4.5Mn; Aluminium 5083-H112; AA5083-H112

Component	Wt. %	Component	Wt. %	Component	Wt. %
Al	92.4 - 95.6	Mg	4 - 4.9	Si	Max 0.4
Cr	0.05 - 0.25	Mn	0.4 - 1	Ti	Max 0.15
Cu	Max 0.1	Other, each	Max 0.05	Zn	Max 0.25
Fe	Max 0.4	Other, total	Max 0.15		

### Material Notes:

Data points with the AA note have been provided by the Aluminum Association, Inc. and are NOT FOR DESIGN.

Physical Properties	Metric	English	Comments
Density	<u>2.66 g/cc</u>	0.0961 lb/in <sup>3</sup>	AA; Typical

### Mechanical Properties

Hardness, Brinell	81	81	500 kg load with 10 mm ball. Calculated value.
Hardness, Knoop	104	104	Converted from Brinell Hardness Value
Hardness, Rockwell B	50	50	Converted from Brinell Hardness Value
Hardness, Vickers	91	91	Converted from Brinell Hardness Value
Tensile Strength, Ultimate	<u>300 MPa</u>	43500 psi	
Tensile Strength, Yield	<u>190 MPa</u>	27600 psi	
Elongation at Break	<u>16 %</u>	16 %	In 5 cm; Sample 1.6 mm thick
Modulus of Elasticity	<u>70.3 GPa</u>	10200 ksi	In Tension

Compressive Modulus	<u>71.7 GPa</u>	10400 ksi	
Poisson's Ratio	0.33	0.33	Estimated from trends in similar Al alloys.
Shear Modulus	<u>26.4 GPa</u>	3830 ksi	
Shear Strength	<u>180 MPa</u>	26100 psi	Calculated value.

### Electrical Properties

Electrical Resistivity	<u>5.9e-006 ohm-cm</u>	5.9e-006 ohm-cm	
------------------------	------------------------	-----------------	--

### Thermal Properties

CTE, linear 68°F	<u>23.8 μm/m-°C</u>	13.2 μin/in-°F	AA; Typical; Average over 68-212°F range.
CTE, linear 250°C	<u>26 μm/m-°C</u>	14.4 μin/in-°F	Average over the range 20-300°C
Specific Heat Capacity	<u>0.9 J/g-°C</u>	0.215 BTU/lb-°F	
Thermal Conductivity	<u>117 W/m-K</u>	812 BTU-in/hr-ft <sup>2</sup> -°F	
Melting Point	591 - 638 °C	1095 - 1180 °F	AA; Typical range based on typical composition for wrought products 1/4 inch thickness or greater
Solidus	<u>591 °C</u>	1095 °F	AA; Typical
Liquidus	<u>638 °C</u>	1180 °F	AA; Typical

### Processing Properties

Annealing Temperature	<u>413 °C</u>	775 °F	holding at temperature not required
Hot-Working Temperature	316 - 482 °C	600 - 900 °F	

### References for this datasheet.

Some of the values displayed above may have been converted from their original units and/or rounded in order to display the information in a consistent format. Users requiring more precise data for scientific or engineering calculations can click on the property value to see the original value as well as raw conversions to equivalent units. We advise that you only use the original value or one of its raw conversions in your calculations to minimize rounding error.