



ASM Aerospace Specification Metals Inc.



Contact Us

Aluminum 5083-H32; 5083-H323

Subcategory: 5000 Series Aluminum Alloy; Aluminum Alloy; Metal; Nonferrous Metal

Close Analogs:

Composition Notes:

Aluminum content reported is calculated as remainder.

Composition information provided by the Aluminum Association and is not for design.

Key Words: UNS A95083; ISO AlMg4.5Mn; Aluminium 5083-H32 and Aluminium 5083-H323; AA5083-H32

Component	Wt. %	Component	Wt. %	Component	Wt. %
Al	92.4 - 95.6	Mg	4 - 4.9	Si	Max 0.4
Cr	0.05 - 0.25	Mn	0.4 - 1	Ti	Max 0.15
Cu	Max 0.1	Other, each	Max 0.05	Zn	Max 0.25
Fe	Max 0.4	Other, total	Max 0.15		

Material Notes:

Data points with the AA note have been provided by the Aluminum Association, Inc. and are NOT FOR DESIGN.

Physical Properties	Metric	English	Comments
Density	<u>2.66 g/cc</u>	0.0961 lb/in ³	AA; Typical

Mechanical Properties

Hardness, Brinell	87	87	500 kg load with 10 mm ball. Calculated value.
Hardness, Knoop	111	111	Converted from Brinell Hardness Value
Hardness, Rockwell A	37.2	37.2	Converted from Brinell Hardness Value
Hardness, Rockwell B	54	54	Converted from Brinell Hardness Value
Hardness, Vickers	98	98	Converted from Brinell Hardness Value
Tensile Strength, Ultimate	<u>320 MPa</u>	46400 psi	
Tensile Strength, Yield	<u>250 MPa</u>	36300 psi	

Elongation at Break	<u>10 %</u>	10 %	In 5 cm; Sample 1.6 mm thick
Modulus of Elasticity	<u>70.3 GPa</u>	10200 ksi	In Tension
Compressive Modulus	<u>71.7 GPa</u>	10400 ksi	
Poisson's Ratio	0.33	0.33	Estimated from trends in similar Al alloys.
Shear Modulus	<u>26.4 GPa</u>	3830 ksi	
Shear Strength	<u>195 MPa</u>	28300 psi	Calculated value.

Electrical Properties

Electrical Resistivity	<u>5.9e-006 ohm-cm</u>	5.9e-006 ohm-cm
------------------------	------------------------	-----------------

Thermal Properties

CTE, linear 68°F	<u>23.8 μm/m-°C</u>	13.2 μin/in-°F	AA; Typical; Average over 68-212°F range.
CTE, linear 250°C	<u>26 μm/m-°C</u>	14.4 μin/in-°F	Average over the range 20-300°C
Specific Heat Capacity	<u>0.9 J/g-°C</u>	0.215 BTU/lb-°F	
Thermal Conductivity	<u>117 W/m-K</u>	812 BTU-in/hr-ft ² -°F	
Melting Point	591 - 638 °C	1095 - 1180 °F	AA; Typical range based on typical composition for wrought products 1/4 inch thickness or greater
Solidus	<u>591 °C</u>	1095 °F	AA; Typical
Liquidus	<u>638 °C</u>	1180 °F	AA; Typical

Processing Properties

Annealing Temperature	<u>413 °C</u>	775 °F	holding at temperature not required
Hot-Working Temperature	316 - 482 °C	600 - 900 °F	

References for this datasheet.

Some of the values displayed above may have been converted from their original units and/or rounded in order to display the information in a consistent format. Users requiring more precise data for scientific or engineering calculations can click on the property value to see the original value as well as raw conversions to equivalent units. We advise that you only use the original value or one of its raw conversions in your calculations to minimize rounding error.