



ASM Aerospace Specification Metals Inc.

Contact Us

## AISI Type S13800 Stainless Steel (PH 13-8 Mo) longitudinal properties, condition H1000

**Subcategory:** Ferrous Metal; Metal; Precipitation Hardening Stainless; Stainless Steel; T S10000 Series Stainless Steel

**Key Words:** UNS S13800, 13-8Mo, 13-8PH, 13-8 PH, 13/8 Mo, 13/8Mo, 13/8PH, 13/8 PH, AMS 5629, AMS 5840, ASME SA705 (XM-13), ASTM A564 (XM-13), ASTM A693 (XM-13), ASTM A705 (XM-13); PH 13-8 Mo; Precipitation Hardening

Component	Wt. %	Component	Wt. %	Component	Wt. %
Al	0.9 - 1.35	Mn	Max 0.1	P	Max 0.01
C	Max 0.05	Mo	2 - 2.5	S	Max 0.008
Cr	12.25 - 13.25	N	Max 0.01	Si	Max 0.1
Fe	76	Ni	7.5 - 8.5		

### Material Notes:

Center or intermediate test location.

Martensitic, precipitation hardening (maraging) stainless steel.

Physical Properties	Metric	English	Comments
Density	<u>7.8 g/cc</u>	0.282 lb/in <sup>3</sup>	

### Mechanical Properties

Tensile Strength, Ultimate	<u>1480 MPa</u>	215000 psi	
Tensile Strength, Yield	<u>1415 MPa</u>	205000 psi	at 0.2% offset
Elongation at Break	<u>13 %</u>	13 %	in 50 mm
Modulus of Elasticity	<u>221 GPa</u>	32100 ksi	
Charpy Impact	<u>54 J</u>	39.8 ft-lb	52 J at room temperature, 41J at 0°C, 27 J at -54°C, 22 J at -73°C, 16 J at -115°C, 9 J at -140°C, 5 J at -195°C
Machinability	35 - 40 %	35 - 40 %	35-40% average, Based on 100% machinability for AISI 1212 steel.

## Electrical Properties

Electrical Resistivity	<a href="#">0.0001 ohm-cm</a>	0.0001 ohm-cm	at 25°C, 0.0001 at 100°C, 0.0001 at 200°C, 0.00011 at 315°C, 0.00011 at 425°C, 0.00011 at 540°C, 0.00011 at 595°C, in Condition A.
------------------------	-------------------------------	---------------	--

## Thermal Properties

CTE, linear 20°C	<a href="#">10.6 μm/m-°C</a>	5.89 μin/in-°F	at 21-95°C, 10.8 at 21-205°C
CTE, linear 250°C	<a href="#">11.2 μm/m-°C</a>	6.22 μin/in-°F	at 21-315°C, 11.3 at 21-425°C
CTE, linear 500°C	<a href="#">11.9 μm/m-°C</a>	6.61 μin/in-°F	at 21-540°C
Specific Heat Capacity	<a href="#">0.46 J/g-°C</a>	0.11 BTU/lb-°F	from 0-100°C (32-212°F)
Thermal Conductivity	<a href="#">14 W/m-K</a>	97.2 BTU-in/hr-ft <sup>2</sup> -°F	at 100°C, 15.7 at 200°C, 17.8 at 315°C, 20.4 at 425°C, 22.3 at 540°C, 22.5 at 595°C; in Condition A.
Melting Point	1405 - 1440 °C	2560 - 2620 °F	
Solidus	<a href="#">1405 °C</a>	2560 °F	
Liquidus	<a href="#">1440 °C</a>	2620 °F	

## References for this datasheet.

Some of the values displayed above may have been converted from their original units and/or rounded in order to display the information in a consistent format. Users requiring more precise data for scientific or engineering calculations can click on the property value to see the original value as well as raw conversions to equivalent units. We advise that you only use the original value or one of its raw conversions in your calculations to minimize rounding error.