



ASM Aerospace Specification Metals Inc.



Contact Us

## Allegheny Ludlum Stainless Steel Type 301, Full Hard (UNS S30100)

**Subcategory:** Ferrous Metal; Metal; Stainless Steel; T 300 Series Stainless Steel

**Key Words:** ASTM A240; ASTM A666

Component	Wt. %	Component	Wt. %	Component	Wt. %
C	Max 0.15	Mn	Max 2	P	Max 0.045
Cr	16 - 18	N	Max 0.1	S	Max 0.03
Fe	75	Ni	6 - 8	Si	Max 0.75

### Material Notes:

Iron content above calculated as balance.

Allegheny Ludlum Type 301 is a high strength grade of steel available in six conditions or tempers, its resistance to atmosphere corrosion and its bright, attractive surface make it an excellent choice for decorative structural applications.

Applications include automobile molding and trim, wheel cover, conveyor belts, kitchen equipment, roof draining systems, hose clamps, springs, truck and trailer bodies, railway and subway cars. By varying the chemical composition within the limits set by the ASTM Specifications and by temper rolling, a broad range of magnetic and mechanical properties can be obtained for a variety of applications.

Information provided by Allegheny Ludlum Corporation.

Physical Properties	Metric	English	Comments
Density	<u>8.03 g/cc</u>	0.29 lb/in <sup>3</sup>	
<b>Mechanical Properties</b>			
Hardness, Brinell	382	382	
Hardness, Rockwell C	41	41	
Tensile Strength, Ultimate	<u>Min 1276 MPa</u>	Min 185000 psi	
Tensile Strength, Yield	<u>Min 965 MPa</u>	Min 140000 psi	0.2% offset
Elongation at Break	<u>Min 9 %</u>	Min 9 %	in 2" (50 mm)

Modulus of Elasticity	<a href="#">174 GPa</a>	25200 ksi	as rolled
Modulus of Elasticity	<a href="#">196 GPa</a>	28400 ksi	stress relieved
Compressive Yield Strength	<a href="#">1317 MPa</a>	191000 psi	transverse
Compressive Yield Strength	<a href="#">793 MPa</a>	115000 psi	longitudinal
Charpy Impact	<a href="#">150 J</a>	111 ft-lb	at 23°C; 150 J at -73°; 150J at 196°
Fatigue Strength	<a href="#">552 MPa</a>	80100 psi	endurance limit; test details not reported

### Electrical Properties

Electrical Resistivity	<a href="#">7.2e-005 ohm-cm</a>	7.2e-005 ohm-cm	
Magnetic Permeability	Max 1.02	Max 1.02	typically < 1.02 at 200H; increases with cold work.

### Thermal Properties

CTE, linear 20°C	<a href="#">16.6 μm/m-°C</a>	9.22 μin/in-°F	Range 20° - 100°C
CTE, linear 250°C	<a href="#">17.6 μm/m-°C</a>	9.78 μin/in-°F	Range 20° - 300°C
CTE, linear 500°C	<a href="#">18.6 μm/m-°C</a>	10.3 μin/in-°F	Range 20°- 500°C; 19.5 μm/m-°C Range 20° - 700°C
Specific Heat Capacity	<a href="#">0.5 J/g-°C</a>	0.12 BTU/lb-°F	between 0° -100° C
Thermal Conductivity	<a href="#">16.3 W/m-K</a>	113 BTU-in/hr-ft <sup>2</sup> -°F	at 100°C; 21.4 W/m*K at 500°C
Melting Point	1399 - 1421 °C	2550 - 2590 °F	
Solidus	<a href="#">1399 °C</a>	2550 °F	
Liquidus	<a href="#">1421 °C</a>	2590 °F	

Some of the values displayed above may have been converted from their original units and/or rounded in order to display the information in a consistent format. Users requiring more precise data for scientific or engineering calculations can click on the property value to see the original value as well as raw conversions to equivalent units. We advise that you only use the original value or one of its raw conversions in your calculations to minimize rounding error.